TECHNICAL DATA

FLEXIBLE MICA PLATE UL Cat. No. SM62 & 8M81

b, teo & co tid

P.O. Box 175 Fo Tan, Shatin, Hong Kong.
Telephone: (852) 2604-8222 * Facsimile: (852) 2693-2093
E-mail: sales@pleo.com * Web Site: http://www.pleo.com



91 UL FILE #E222948

Description:

SM 62 & 8M81 is a flexible Silicone bonded mica paper which retains its flexibility permanently has two species. It is made of silicone bonded mica plate with specially formulated silicone resin. is **UL94V-0 RTI 200°C approval with UL file No. E222948.** It is widely used for class H, class C, Class R and Class S insulation of high voltage transformer for microwave oven, thermal barrier for home appliances, dry type transformer and industrial furnace

Application:

SM61 & 8M81 series are flexible and can be permitted winding or wrapping into place without heating. They are used as linings, covers or backings, as a separating sheet or insulating sheet, application is: Heat gun, Hair dryers, Fan heaters, Circuit breakers, Transformers, Electric furnaces, Generator, Magnetic Coil Insulation etc.

Properties:

- Excellent resistance to heat up to 1000 °C
- Excellent Electrical Insulation
- Excellent tensile strength and easy to form at room temperature

Technical Data:

	<u>UNIT</u>	SM62/8M81	<u>SM61</u>	
Mica paper		Muscovite	Phlogopite	
Thickness	mm	0.15 - 3.0	0.15 - 3.0	
Thickness Tolerance	mm	$\pm10\%$	$\pm 10\%$	
Density	g/cm ³	ca. 2.0	ca. 2.0	
Mica Content	%	>ca. 90	>ca. 90	
Bond Content	%	<ca. 90<="" td=""><td><ca. 90<="" td=""></ca.></td></ca.>	<ca. 90<="" td=""></ca.>	
Dielectric Strength	kV/mm	>20	>20	
Heat Resistance:				
Continuous Services	°C	500	700	
Intermittent Service	°C	800	1000	
Heat loss at 500°C	%	<1	<1	
Heat loss at 700°C	%	<2	<2	
Sheet Size	mm	1000 x 1200 / 1000x 2400 /1000 x 600		
		Test Procee	Test Procedure IEC 371-2	



BCtape[™] Phobbin® BCwire® BCmica® BCtube® is P. Leo & Co., (B.C.) Ltd. registered trade mark

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness there of is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer shall be liable for any nijury loss or damage direct or consequential arising out of the use of or *he inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection there with.